
## FFEH - Full Flat Element Hollow TC/K



## **Properties**

The standard range of ceramic infrared elements in stock are used in a wide range of industrial and engineering applications such as thermoforming, packaging, paint curing, printing, drying, gluing, sterilisation, roasting etc. They are also very effectively used in infrared outdoor heaters and saunas.


Most plastics and many other materials absorb infrared best in the wavelength range of  $\,$  2-10  $\mu m$ , which makes the ceramic heater the most popular radiant emitter on the market.



## **Technical specification**


Material	Ceramic solid body in white glaze colour with an embedded resistance heating coil	
Heater Voltage	230 V (standard)	
Operating Temperature	Max permissible 750°C	
Useful wave-length range	2 - 10 μm (microns) long wavelength	
Dimensions	245 x 60 x 37.5 mm	
Average weight	266 g	
Electric connection	120 mm ceramic beaded power leads	
Assembly	Recommended radiation distance from heater is 100mm to 200mm. Mounting slot size oval 15x42 mm Steel wave spring and clip set included	
Recommended Spacing	5mm minimum spacing between elements	
Average operating life	Up to 20 000 hrs depending on conditions	
Standards	CE	
Packaging w x h x d	252 x 64 x 64 mm	






## Standard assortment

Model	Power	Mean Surface	Max Power
FFEH	W	Temperature °C	Density kW/m²
FFEH 250	250	390	15
FFEH 300	300	419	19
FFEH 400	400	497	24
FFEH 600	600	602	36
FFEH 800	800	710	48





Heating up and cooling down curves showing average surface temperature taken with an infrared thermometer set at an emissivity of 0.95 ( Element mounted in an aluminised steel reflector RAS )